(11) **EP 1 216 746 A2**(12) **EUROPEAN PATENT APPLICATION**(43) Date of publication:
26.06.2002 Bulletin 2002/26(51) Int Cl.7: **B01D 53/94, B01J 23/755,
F01N 3/08, B01D 53/32,
B01J 19/08**(21) Application number: **01204810.4**(22) Date of filing: **10.12.2001**(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

- Fisher, Galen Bruce
Bloomfield Hills, MI 48301 (US)
- Labarge, William J.
Bay City, MI 48706 (US)

(30) Priority: **21.12.2000 US 745849**(71) Applicant: **Delphi Technologies, Inc.**
Troy, MI 48007 (US)(74) Representative: **Denton, Michael John et al**
Delphi Automotive Systems,
Centre Technique Paris,
117, avenue des Nations,
B.P. 60059
95972 Roissy Charles de Gaulle Cédex (FR)(72) Inventors:
• Kupe, Joachim
Davisburg, MI 48350 (US)(54) **NO_x adsorbent with SO_x poisoning protection**

(57) A NO_x control (20) for an exhaust is provided. The NO_x control (20) includes a nickel compound and a NO_x adsorber. The NO_x adsorber is suitable for a high oxygen content exhaust, such as an exhaust from a compression-ignition engine or a lean-burn spark-ignition engine having oxygen content greater than about 1 molar% based on the total exhaust. Systems (10 or 50) for treating an exhaust gas (16 or 56) are also provided, including use of a non-thermal plasma reactor (14) and a NO_x control (20), or use of a first non-thermal plasma reactor (54), a particulate trap (60), a second non-ther-

mal plasma reactor (60), and a NO_x control (20). Additionally, methods for forming a NO_x control (20) are also described, comprising either mixing, milling, or sintering a nickel compound integrally with a NO_x adsorber, or processing a nickel compound with a NO_x adsorber by mixing, milling, or sintering, washcoating, imbibing, impregnating, physisorbing, chemisorbing, precipitating, vapor depositing, or any combination of at least one of the foregoing processing techniques

EP 1 216 746 A2

1

EP 1 216 746 A2

2

Description**TECHNICAL FIELD**

[0001] The present disclosure relates to NO_x controls.

BACKGROUND

[0002] The reduction of nitrogen oxide (NO_x), e.g., nitric oxide (NO), nitrogen dioxide (NO₂), and nitrous oxide (N₂O), in exhaust gas is a widely addressed problem as a result of environmental concerns and mandated government emissions regulations, particularly in the transportation industry. One approach uses three-way conversion catalysts to treat the exhaust gases of spark-ignited gasoline internal combustion engines for the reduction of NO_x emission, since the exhaust contains minimal oxygen.

[0003] However, fuel economy and global carbon dioxide (CO₂) emission concerns have made it desirable to operate engines under lean-burn conditions to realize a benefit in fuel economy. Under such conditions, the exhaust streams contain excessive oxygen, and accordingly, conventional three-way conversion catalysts are generally inefficient in the reduction of nitrogen oxides. For example, a lean burn engine exhaust stream has from about 1% to 10% excess oxygen relative to the amount of fuel. Further, exhaust streams of compression-ignition engines such as diesel engines also have high oxygen content. For example, the exhaust stream may contain from perhaps about 2-20 molar% oxygen based on the total exhaust, and, in addition, contains a significant amount of particulate emissions.

[0004] Hydrocarbon (HC), particulate, or NO_x emissions from an exhaust or effluent stream may be treated with a non-thermal plasma reaction in conjunction with a NO_x catalyst, adsorber, or storage compound. Typically, the various NO_x compounds are converted to NO₂, which, in the presence of HCs and water, is converted into nitrogen gas (N₂), oxygen gas (O₂), carbon dioxide (CO₂).

[0005] In addition to the NO_x, the exhaust gases typically contain sulfur compounds such as sulfur dioxide (SO₂) gas and particulate sulfate (SO₄), which are produced by the burning of sulfur contained in the fuel. The NO_x catalyst oxidizes SO₂ to sulfur trioxide (SO₃) in oxygen-rich atmospheres. Still further, SO₃ reacts readily with water vapor, which is also contained in the exhaust gases, to produce sulfite ions and sulfate ions. The sulfite ions and sulfate ions react with the NO_x catalyst to produce sulfites and sulfates. The resulting sulfites and sulfates adversely affect the NO_x storage reaction. Thus, such sulfites and sulfates are commonly referred to as NO_x poisons.

[0006] Therefore, as is apparent from the above brief description of NO_x removal, such NO_x poisons result in degraded exhaust purification. What is needed in the art

is a sulfur resistant NO_x catalyst.

SUMMARY

[0007] The above-described and other disadvantages of the prior art are overcome by the system wherein a NO_x control for an exhaust is provided. The NO_x control includes a nickel compound in conjunction with a NO_x adsorber. The NO_x adsorber is generally suitable for a high oxygen content exhaust, such as an exhaust having oxygen content greater than about 1 molar% based on the total exhaust.

[0008] Further, a system for treating an exhaust gas includes a non-thermal plasma reactor and a NO_x control. The NO_x control includes a nickel compound in conjunction with a NO_x adsorber, which is generally suitable for a high oxygen content exhaust, such as an exhaust having oxygen content greater than about 1 molar% based on the total exhaust.

[0009] Still further, a system may also contain a first non-thermal plasma reactor, a particulate trap, a second non-thermal plasma reactor, and a NO_x control.

[0010] A method for poison protection in an engine exhaust is also provided, wherein an exhaust gas is exposed to a NO_x control which includes a nickel compound in conjunction with a NO_x adsorber, which is generally suitable for a high oxygen content exhaust, such as an exhaust having oxygen content greater than about 1 molar% based on the total exhaust. The exhaust gas for this method typically contains greater than about 1 molar% oxygen based on the total exhaust.

[0011] Further, methods for forming a NO_x control are also described, comprising either mixing, milling, or sintering a nickel compound integrally with a NO_x adsorber, or processing a nickel compound with a NO_x adsorber by mixing, milling, or sintering, washcoating, imbibing, impregnating, physisorbing, chemisorbing, precipitating, vapor depositing, or any combination of at least one of the foregoing processing techniques.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] For a further understanding of the nature of the present invention, as well as other features and advantages thereof, reference should be made to the following detailed description taken in conjunction with the accompanying drawings, which are meant to be exemplary not limiting, and wherein like elements are numbered alike in the several figures.

Figure 1 is a schematic of a NO_x reduction system.
Figure 2 is a schematic of another NO_x reduction system.

DESCRIPTION OF THE PREFERRED EMBODIMENT

[0013] A NO_x adsorber or a NO_x adsorber system comprises a nickel or nickel oxide (NiO) component as

3

EP 1 216 746 A2

4


a protective portion to minimize poisoning of the NO_x adsorber material or the NO_x adsorber by sulfur compounds.

[0014] Referring now to Figure 1, a schematic of a NO_x reduction system 10 is detailed. The NO_x reduction system 10 includes a non-thermal plasma reactor 14 that receives a contaminated exhaust 16, for example, from a spark-ignition or compression-ignition engine 12. The contaminated exhaust typically comprises oxygen, HCs, NO_x, and possibly other contaminants including, but not limited to, sulfur compounds (e.g., SO₂, SO₄) and particulate carbon. Under oxidizing conditions, the contaminated exhaust 16 may comprise about 1% to about 20%, or even up to about 30%, oxygen.

[0015] The non-thermal plasma reactor 14 generally converts the various NO_x compounds into NO₂. A partially cleaned gas stream 18 exits the plasma reactor 14 and is introduced into a NO_x control 20 generally for decomposing HCs and NO_x into O₂, CO₂, H₂O, and N₂ with clean exhaust 22 exiting the NO_x control 20.

[0016] Plasma reactor 14 is capable of generating a potential for ionizing gasses. The plasma reactor 14 is typically connected to a power supply and comprises a system for generating a non-thermal plasma. The plasma includes a mixture of reactive free radicals, ions, and electrons that cause conversion or partial conversion of HCs, oxygen, and certain NO_x compositions, as well as neutral species.


[0017] A non-thermal plasma can be generated between a pair of electrodes by a number of methods, including electrical fields, electron beams, and irradiation with electromagnetic energy of appropriate intensity and wavelength. Electrical field plasma can be generated with a high voltage (e.g., about 10,000 volts) electrical field suitable for the gas and gap geometry. A local dissociation of electrons results, and the electrons accelerate rapidly in the electrical field. The accelerating electrons strike and ionize other molecules. If the voltage is stopped before or shortly after a streamer (equivalent to the path of ionized molecules and electrons) crosses the gas gap causing an arc discharge, then a non-thermal plasma of ions and free electrons is formed. For example, oxygen gas (O₂) is ionized into ozone (O₃) according to the following reaction:



The NO_x components, particularly nitric oxide, react in the presence of ozone as follows:



Further, due to the ozone, some of the SO₂ present is converted to SO₃ generally as follows:



[0018] Certain configurations for the plasma reactor 14 include that of a dielectric barrier reactor, an electrified packed bed reactor, a glow-discharge plasma reactor, a corona discharge reactor, and other suitable plasma reactors. In the various plasma reactor types and geometries, the discharges that create the plasma originate at the surface of the electrodes at a point where the peak electric field strength is at least about five times that of the average energy field (a discharge point). Thus, preferably the reactor has a sufficient number of such discharge points positioned so as to substantially uniformly treat the target emissions in the exhaust stream.

[0019] For example, when employing a dielectric barrier reactor's plasma reactor 14, one or both electrodes are coated with a dielectric material, e.g., flat alumina plates screen printed with a dielectric such as a copper chrome alloy ink coating. During operation, a streamer is formed by an electron accelerating in the electric field, with the streamer extinguished on the surface of the dielectric material. From the plasma reactor 14, the exhaust enters NO_x control 20. NO_x control 20, which is particularly suited for oxidized exhausts having oxygen content of greater than 1, 2, 5, 10, 20, or even 30 molar% based on the total exhaust (wherein the oxidized exhaust comprises greater than 1% oxygen is referenced as "high oxygen content"), comprises a nickel compound and a NO_x active material such as a NO_x adsorber. The nickel compound, which may comprise a brick, or a mixture such as a coating or an integral mixture on the NO_x adsorber, can comprise pure nickel oxide (NiO) or a mixture, alloy, composite, or cermet of NiO and metals, metal oxides, ceramics, binders, fugitive materials, combinations thereof, and the like. Some possible materials which can be combined with the NiO include copper oxide, silver oxide, chrome oxide, as well as mixtures, alloys, composites, and cermets comprising at least one of the foregoing materials.

[0020] The nickel compound can comprise about 1 weight percent (wt.%) to about 100 wt% NiO, preferably about 50 wt% to about 100 wt% NiO, and more preferably about 80 wt% to about 100 wt% NiO, based on the total weight of the nickel compound.

[0021] The compound composition is provided in various forms during manufacture, including: solid, for processes such as mixing, milling, or sintering, and the like; liquid solution, for processes such as washcoating, imbibing, impregnating, physisorbing, chemisorbing, precipitating, and the like; gaseous composition, for processes such as vapor depositing, and the like; or any combination of phases.

[0022] In one embodiment, a nickel compound coating is formed on a support material independent from the NO_x catalyst material, generally in sufficient quantity to promote reduction of NO_x poisonous species. For

3

5

EP 1 216 746 A2

6

most automotive applications, a sufficient quantity of nickel compound is about 0.125 milligrams per square centimeter (mg/cm^2) to about $0.512 \text{ mg}/\text{cm}^2$, with about $0.256 \text{ mg}/\text{cm}^2$ to about $0.384 \text{ mg}/\text{cm}^2$ of nickel compound preferred. The coating composition may be mixed, milled, sintered, washcoated, imbibed, impregnated, physisorbed, chemisorbed, precipitated, vapor deposited, otherwise applied, or processed by any combination of at least one of the foregoing processing techniques, integrally with the support material.

[0023] The support material can comprise any material: designed for use in a spark-ignition or compression-ignition environment (e.g., temperature of about -40°C to about $1,000^\circ\text{C}$; capable of withstanding exposure to HCs, nitrogen oxides, carbon monoxide, carbon dioxide, carbonaceous soot, and/or sulfur; and having sufficient surface area and structural integrity to support the desired coating composition. Preferably, the support material has a surface area up to or exceeding about 600 squared meters per gram (m^2/g). Some possible support materials include, but are not limited to, alumina (e.g., gamma-alumina, delta-alumina, theta-alumina, and the like), zeolite, zirconium, cerium, cesium, magnesium, titanium, silicon, cordierite, silicon carbide, porous glasses, metallic foils, mullite, alkali and alkaline-earth zirconium phosphates (NZP), and combinations, alloys, oxides, and cermets comprising at least one of these materials, among others.

[0024] Although the support materials can have any size or geometry, the size and geometry are preferably chosen to optimize surface area in the given design parameters. Suitable support materials are in the form of mesh, corrugated foils, layered materials, spun fibers, extrudates, spheres, beads, tablets, ceramic foams, and monoliths. In one embodiment, the support material comprises a monolith (ceramic or metallic) having a honeycomb geometry, with the combs through-channel having any multi-sided or rounded shape, with substantially square, triangular, pentagonal, hexagonal, heptagonal, or octagonal or similar geometries preferred due to ease of manufacturing and increased surface area.

[0025] In addition to formation on a support material, the nickel compound may be provided as a self-supported structure suitable for placement within a gas stream. For example, a nickel compound may be formed into a brick or a porous compact which forms at least a portion of the NO_x control 20.

[0026] Although the nickel compound is preferably employed in a NO_x control 20 disposed upstream of the NO_x adsorber, the nickel compound can be employed integrally with the NO_x adsorber. The nickel compound may be mixed, milled, sintered, washcoated, imbibed, impregnated, physisorbed, chemisorbed, precipitated, vapor deposited, otherwise applied, or processed by any combination of at least one of the foregoing processing techniques with the NO_x adsorber. Preferably, the NO_x control 20 is formed by adding the nickel compound to the NO_x adsorber in a manner so as not

to occupy active sites intended for NO_x reduction. The protective nickel compound coating acts as a poison trap, generally preventing or minimizing the possibility of sulfur and other contaminants occupying or otherwise deactivating the NO_x catalyst material.

[0027] The NO_x adsorber may comprise one or more catalyst materials integral with a support material, such as those described above for supporting the nickel compound. Possible NO_x catalysts comprise those materials capable of reducing NO_x to N_2 and various oxygen containing compounds (e.g., CO_2 , H_2O , and the like). For example, these materials include cesium, barium, lanthanum, silver, zirconium, zeolites, alumina, silicon, manganese, as well as alloys, oxides, and combinations comprising at least one of the foregoing materials. Further, the NO_x catalyst system preferably comprises a material active in an oxygen rich environment including lean burn spark-ignition engines, or compression-ignition engines such as diesel engines. Such oxygen rich environments may comprise exhaust streams including up to about 30% oxygen. Additionally, the NO_x catalyst system preferably comprises a material active in temperature ranges less than about 500°C , and more preferably active in temperature ranges less than about 150°C (i.e., the light-off temperature).

[0028] Referring now to Figure 2, a NO_x reduction system 50 is detailed. The NO_x reduction system 50 includes a first non-thermal plasma reactor 54 that receives a high oxygen content contaminated exhaust 56, for example, from a spark-ignition or compression-ignition engine 52. The contaminated exhaust typically comprises oxygen, HCs, NO_x , and other contaminants including but not limited to sulfur compounds (e.g., SO_2 , SO_4) and particulate carbon. The first plasma reactor 54 partially or completely converts HCs, NO to NO_2 , oxygen to ozone, among other ionizations, resulting in a partially cleaned exhaust 58 that is introduced to a particle trap 60. Within particle trap 60, carbonaceous and sulfate particles are trapped. Some of the carbonaceous particles react with a portion of the NO_2 to form carbon monoxide (CO) and reconvert NO_2 to NO, which exit in an exhaust 62. The exhaust 62, generally comprising oxygen, ozone, HCs, NO, and NO_2 , is fed into a second plasma reactor 66, where NO is converted to NO_2 . The exhaust 68, generally comprising oxygen, ozone, HCs, and NO_2 , is converted in a NO_x control 20 to water, oxygen, molecular nitrogen, and carbon dioxide which exits NO_x control 20 as clean exhaust 72.

[0029] In use, NO_x compounds are converted and adsorbed in sites on the NO_x adsorber. Further, the nickel compound attracts sulfur, as described further herein. Therefore, the NO_x control 20 may be operatively coupled to a desorbing mechanism (not shown) for extended usage. In certain systems, the temperature levels rise sufficiently for nickel to release sulfur compounds and for NO_x compounds to release from the NO_x adsorber (e.g., about 500°C), thus the NO_x control 20 may passively desorb. In other systems, for example, where-

7

EP 1 216 746 A2

8

In the temperature levels do not rise above 500°C, desorption may be accomplished by an active mechanism. The active desorption mechanism may comprise heat, a plasma reactor, or other suitable desorption mechanism.

EXAMPLES

[0030] The following examples illustrate specific NO_x controls. It should be understood that the examples are given for the purpose of illustration and are not intended as limitations. In the examples, all parts and percentages are by weight based on the total weight of the composition unless otherwise specified.

Example 1

[0031] Zeolite with a silica to alumina ratio of 5 was triple exchanged with barium nitrate, wherein each calcining step was at 740°C for 2 hours. The resulting mixed oxide was about 18 wt% barium. The barium-zeolite was mixed with nickel 2-ethyl hexanoate, and calcined at 500°C. The result was a stabilized barium-zeolite (Ba-Si₂O₃/Al₂O₃) encapsulated in a poison protective layer of NiO. The nickel oxide-barium-zeolite was dispersed with water containing 2 wt% nitric acid, and the resulting slurry was coated on a 600 cells per cubed inch (cell/in³) cordierite monolith. The wash-coated monolith was calcined at 500°C for 2 hours.

Example 2

[0032] Zeolite was triple exchanged with barium nitrate as in Example 1. About 80 wt% barium-zeolite was mixed with about 20 wt% nickel oxide. The nickel oxide had a surface area of at least about 100 m²/g. The nickel oxide-barium-zeolite was dispersed with water containing 2 wt% nitric acid, and the resulting slurry was coated on a 600 cell/in³ cordierite monolith. The wash-coated monolith was calcined at 500°C for 2 hours.

Example 3

[0033] A first 600 cell/in³ cordierite monolith of a two monolith system was coated with 100 wt% nickel oxide having a surface area of at least 100 m²/g. The coated first monolith was calcined at 500°C for 2 hours. A second 600 cell/in³ cordierite monolith of the two monolith system was coated with composition of zeolite triple exchanged with barium nitrate (as in Example 1).

Example 4

[0034] A first layer of a dual layer washcoat was zeolite triple exchanged with barium nitrate as in Example 1, which was coated on a 600 cell/in³ cordierite monolith. A second layer of the dual layer washcoat system was 100 wt% nickel oxide having a surface area of at

least 100 m²/g, which was coated over the first layer on the monolith. The dual layer washcoated monolith was calcined at 500°C for 2 hours.

Example 5

[0035] Zeolite was triple exchanged with barium nitrate as in Example 1. The barium-zeolite was mixed with nickel 2-ethyl hexanoate. The resulting mixture was calcined at 500°C. The result was a stabilized barium-zeolite (Ba-Si₂O₃/Al₂O₃) encapsulated with a poison protective layer of NiO. About 70 wt% nickel oxide-barium-zeolite and 30% gamma-alumina was dispersed with water containing 2 wt% nitric acid. The resulting slurry was coated on a 600 cell/in³ cordierite monolith. The wash-coated monolith was calcined at 500°C for 2 hours.

Example 6

[0036] Zeolite was triple exchanged with barium nitrate as in Example 1. About 60 wt% barium-zeolite was mixed with 15 wt% nickel oxide having a surface area of at least 100 m²/g and 25 wt% gamma alumina. The nickel oxide-barium-zeolite-alumina was dispersed with water containing 2 wt% nitric acid, and the resulting slurry was coated on a 600 cell/in³ cordierite monolith. The wash-coated monolith was calcined at 500°C for 2 hours.

Example 7

[0037] A first 600 cell/in³ cordierite monolith of a two monolith system was coated with 100 wt% nickel oxide having a surface area of at least 100 m²/g and calcined at 500°C for 2 hours. A second 600 cell/in³ cordierite monolith of a two monolith system was coated with 75 wt% barium-zeolite and 25 wt% gamma alumina. The monolith was calcined at 500°C for 2 hours.

Example 8

[0038] A first layer of a dual layer washcoat included 75 wt% zeolite and 25 wt% alumina, which was coated on a 600 cell/in³ cordierite monolith. The coated monolith was calcined at 500°C for 2 hours. A second layer of a dual layer washcoat system included 100 wt% nickel oxide having a surface area of at least 100 m²/g that was coated over the first layer on the monolith. The dual layer washcoated monolith was calcined at 500°C for 2 hours.

Example 9

[0039] Barium oxide was mixed with nickel 2-ethyl hexanoate, and calcined at 500°C. The result was barium oxide encapsulated with a poison protective layer of NiO. The nickel oxide-barium oxide was dispersed

5

9

EP 1 216 746 A2

10

with water containing 2 wt% nitric acid, and the resulting slurry was coated on a 600 cell/in² cordierite monolith. The wash-coated monolith was calcined at 700°C for 2 hours.

Example 10

[0040] About 80 wt% barium oxide was mixed with 20 wt% nickel oxide having a surface area of at least 100 m²/g. The nickel oxide-barium-oxide was dispersed with water containing 2 wt% nitric acid, and the resulting slurry was coated on a 600 cell/in² cordierite monolith. The wash-coated monolith was calcined at 700°C for 2 hours.


Example 11

[0041] A first 600 cell/in² cordierite monolith of a two monolith system was coated with 100 wt% nickel oxide having a surface area of at least 100 m²/g. The coated first monolith was calcined at 500°C for 2 hours. The second 600 cell/in² cordierite monolith of the two monolith system included 100 wt% barium oxide. The coated second monolith was calcined at 740°C for 2 hours.


Example 12

[0042] A first layer of a dual layer washcoat comprising 100 wt% barium oxide was coated on a 600 cell/in² cordierite monolith. The coated monolith was calcined at 740°C for 2 hours. A second layer of a dual layer washcoat system included 100 wt% nickel oxide having a surface area of at least 100 m²/g that was coated over the first layer on the monolith. The dual layer washcoated monolith was calcined at 500°C for 2 hours.


[0043] In a typical system not including the nickel composition poison trap, a NO_x catalyst system include barium impregnated zeolite. In oxygen rich environments, barium oxide is formed, which generally reacts with NO₂ to form barium nitrate, as follows:



Barium nitrate reacts with the existing HCs, resulting in water, elemental nitrogen, and carbon dioxide as follows:




However, in the presence of sulfur trioxide (SO₃), barium oxide also typically reacts to form barium sulfate:



The formation of barium sulfate (BaSO₄) is typically ir-

reversible in systems operating at less than about 500°C. Thus, the NO_x activity correspondingly decreases.

[0044] The inclusion of the nickel compound poison trap causes the sulfur trioxide to react with nickel (or NiO), rather than the barium (or other catalyst) composition. The nickel compositions used preferably have a strong affinity for sulfates. Particularly, NiO reacts readily with sulfur trioxide, which is generally formed due to reaction of ozone and sulfur dioxide as described above. Sulfur trioxide is reacted as follows at the nickel coating trap:



[0045] In exhaust systems that have a low oxygen content (e.g., less than about 1 molar% based on the total exhaust), nickel compounds are typically avoided or used in small quantities, e.g., less than about 2 wt.%. The lack of oxygen causes adverse poisoning of the NO_x adsorber. Generally, in neutral or reducing conditions, the nickel oxide will minimally release trapped sulfur. Also, in high temperature environments, the high temperature will decrease the active surface area of the nickel oxide, but the benefits of the nickel oxide described herein are essentially unaffected up to about 800°C. Higher temperatures will further cause irreversible formation of NiAl₂O₄ or other inactive compounds. Furthermore, use of nickel compounds with conversion catalysts employing precious metals such as platinum, palladium, and rhodium may coat the surface of the precious metal, thus such usage is preferably minimized to reduce waste of such precious metal compounds.

[0046] Consequently, nickel compounds, provided either separate from or in combination with a support or a catalyst, provides several benefits to typical exhaust systems. One primary benefit is the trapping of poisons (i.e., constituents that may be detrimental to the life of the catalysts or that may bypass catalyst conversion) such as phosphorous, sulfur, halogens, silicon, and other poisons. Further, nickel compounds, particularly NiO, may have NO_x reduction activity; may facilitate organic decomposition by dehydrogenating organics (e.g., dehydrogenating butane to more reactive organics such as butene) and by cracking heavy organics into more reactive lighter organics; and may reduce the amount of sulfated particulates.

[0047] While preferred embodiments have been shown and described, various modifications and substitutions may be made thereto without departing from the spirit and scope of the invention. Accordingly, it is to be understood that the system and method have been described by way of illustration only, and such illustrations and embodiments as have been disclosed herein are not to be construed as limiting to the claims.

11

EP 1 216 746 A2

12

Claims

1. A NO_x control (20) for an exhaust comprising:

a nickel compound and a NO_x adsorber, where-
in the NO_x adsorber is selected for an oxygen
content in said exhaust greater than about 1
molar% based on the total exhaust.

2. The NO_x control (20) as in Claim 1, wherein said
nickel compound comprises nickel oxide.

3. The NO_x control (20) as in Claim 2, wherein said
nickel compound comprises about 1% to about
100% nickel oxide based on total weight of the nick-
el composition.

4. The NO_x control (20) as in Claim 2, wherein said
nickel compound comprises about 50% to about
100% nickel oxide based on total weight of the nick-
el composition.

5. The NO_x control (20) as in Claim 2, wherein said
nickel compound comprises about 80% to about
100% nickel oxide based on total weight of the nick-
el composition.

6. The NO_x control (20) as in Claim 1, wherein said
nickel compound comprises a coating on said NO_x
adsorber.

7. The NO_x control (20) as in Claim 1, wherein said
nickel compound comprises a plurality of particu-
lates dispersed throughout said NO_x adsorber.

8. The NO_x control (20) as in Claim 1, wherein said
nickel compound comprises a coating on said NO_x
catalyst system and further comprises a plurality of
particulates dispersed throughout said NO_x ad-
sorber.

9. The NO_x control (20) as in Claim 1, wherein said
nickel compound is formed on a first support, and
further wherein said NO_x adsorber is formed on a
second support independent from said first support.

10. The NO_x control (20) as in Claim 9, wherein said
nickel compound is configured for positioning in
said exhaust upstream from said NO_x adsorber.

11. The NO_x control (20) as in Claim 1, wherein said
nickel compound is formed as a structure, and fur-
ther wherein said NO_x adsorber is formed on a sup-
port, said support being independent from said
structure.

12. The NO_x control (20) as in Claim 1, wherein said
NO_x adsorber comprises a catalyst material and a

support, said catalyst material selected from the
group consisting of cesium, barium, lanthanum, sil-
ver, zirconium, and alloys, oxides, and combina-
tions comprising at least one of the foregoing cata-
lyst materials.

13. A system (10) for treating an exhaust gas (16) com-
prising:

a non-thermal plasma (14) reactor; and
a NO_x control (20) comprising a nickel com-
pound and a NO_x adsorber, wherein the NO_x
adsorber is selected for an oxygen content in
said exhaust greater than about 1 molar%.

14. A system (50) for treating an exhaust gas (56) com-
prising:

a first non-thermal plasma reactor (54);
a particulate trap (60);
a second non-thermal plasma reactor (66); and
a NO_x control (20) comprising a nickel com-
pound and a NO_x adsorber, wherein the NO_x
adsorber is selected for an oxygen content in
said exhaust greater than about 1 molar%.

15. A method for poison protection in an engine exhaust
(16), comprising:

exposing said exhaust (16) having an oxygen
content greater than about 1 molar% to a NO_x
control (20) comprising a nickel compound and
a NO_x adsorber, wherein the NO_x adsorber is
selected for an oxygen content in said exhaust
greater than about 1 molar%.


16. A method for forming a poison protection compo-
nent in a NO_x control (20), comprising:

mixing, milling, or sintering a nickel compound
integrally with a NO_x adsorber.


17. A method for forming a poison protection compo-
nent in a NO_x control (20), comprising:

processing a nickel compound with a NO_x ad-
sorber by mixing, milling, sintering, washcoat-
ing, imbibing, impregnating, physisorbing,
chemisorbing, precipitating, vapor depositing,
or any combination of at least one of the fore-
going processing techniques.

EP 1 216 746 A2



EP 1 216 746 A2



(11) **EP 1 216 746 A3**(12) **EUROPEAN PATENT APPLICATION**(88) Date of publication A3:
24.07.2002 Bulletin 2002/30(51) Int Cl.7: **B01D 53/94, B01J 23/755,**
F01N 3/08, B01D 53/32,
B01J 19/08(43) Date of publication A2:
26.06.2002 Bulletin 2002/26(21) Application number: **01204810.4**(22) Date of filing: **10.12.2001**(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
 Designated Extension States:
AL LT LV MK RO SI

- Fisher, Galen Bruce
 Bloomfield Hills, MI 48301 (US)
- Labarge, William J.
 Bay City, MI 48706 (US)

(30) Priority: **21.12.2000 US 745849**(71) Applicant: **Delphi Technologies, Inc.**
Troy, MI 48007 (US)(74) Representative: **Denton, Michael John et al**
Delphi Automotive Systems,
Centre Technique Paris,
117, avenue des Nations,
B.P. 60059
95972 Roissy Charles de Gaulle Cédex (FR)(72) Inventors:

- Kupe, Joachim
 Davisburg, MI 48350 (US)

(54) **NO_x adsorbent with SO_x poisoning protection**

(57) A NO_x control (20) for an exhaust is provided. The NO_x control (20) includes a nickel compound and a NO_x adsorber. The NO_x adsorber is suitable for a high oxygen content exhaust, such as an exhaust from a compression-ignition engine or a lean-burn spark-ignition engine having oxygen content greater than about 1 molar% based on the total exhaust. Systems (10 or 50) for treating an exhaust gas (16 or 56) are also provided, including use of a non-thermal plasma reactor (14) and a NO_x control (20), or use of a first non-thermal plasma reactor (54), a particulate trap (50), a second non-ther-

mal plasma reactor (60), and a NO_x control (20). Additionally, methods for forming a NO_x control (20) are also described, comprising either mixing, milling, or sintering a nickel compound integrally with a NO_x adsorber, or processing a nickel compound with a NO_x adsorber by mixing, milling, or sintering, washcoating, impregnating, physisorbing, chemisorbing, precipitating, vapor depositing, or any combination of at least one of the foregoing processing techniques.

EP 1 216 746 A3

Printed by Jouve, 75001 PARIS (FR)

EP 1 216 746 A3

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 20 4810

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 878 610 A (MITSUBISHI MOTORS CORP) 18 November 1998 (1998-11-18) * column 2, line 43 - column 3, line 22 * * column 6, line 29 - line 49 * * column 8, line 43 - line 50 * * column 9, line 10 - line 22; claim 1; figure 6 *	1-12, 15-17	B01D53/94 B01J23/755 F01N3/08 B01D53/32 B01J19/08
Y	---	13,14	
X	EP 0 905 354 A (MAZDA MOTOR) 31 March 1999 (1999-03-31) * page 1, line 48 - page 2, line 18 * * page 7, line 49 - page 8, line 6; claims 1,3,7; figure 7 *	1-12, 15-17	
X	EP 0 625 633 A (TOYOTA MOTOR CO LTD) 23 November 1994 (1994-11-23) * column 9, line 40 - column 10, line 19 * * column 27, line 45 - column 28, line 6 * * column 29, line 50 - column 30, line 5; claims 1-6; figure 1 *	1-12, 15-17	
X	EP 0 664 147 A (TOYOTA MOTOR CO LTD) 26 July 1995 (1995-07-26) * page 3, line 50 - page 4, line 22; claims 4,5; figures; table 2 *	1-12, 15-17	B01D B01J F01N
Y	EP 0 953 375 A (DEGUSSA) 3 November 1999 (1999-11-03) * claims; figure 4 *	13	
Y	WO 00 43102 A (SHAWCROSS JAMES TIMOTHY; RAYBONE DAVID (GB); AEA TECHNOLOGY PLC (G)) 27 July 2000 (2000-07-27) * page 12, line 11 - page 15, line 27; claims; figure *	14	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 27 May 2002	Examiner Eijkenboom, A
CATEGORY OF CITED DOCUMENTS X : part clearly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document 1 : theory or principle underlying the invention 2 : earlier patent document, not published on, or after the filing date 3 : document cited in the application 4 : document cited for other reasons 5 : member of the same patent family, corresponding document			

EP 1 216 746 A3

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 01 20 4810

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-05-2002

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0878610	A	18-11-1998	JP	10317946 A	02-12-1998
			EP	0878610 A1	18-11-1998
EP 0905354	A	31-03-1999	JP	11156159 A	15-06-1999
			EP	0905354 A2	31-03-1999
EP 0625633	A	23-11-1994	JP	2605559 B2	30-04-1997
			JP	6173652 A	21-06-1994
			JP	2605571 B2	30-04-1997
			JP	6229232 A	16-08-1994
			JP	2605580 B2	30-04-1997
			JP	6346768 A	20-12-1994
			DE	69328083 D1	20-04-2000
			DE	69328083 T2	08-02-2001
			EP	0625633 A1	23-11-1994
			WO	9412778 A1	09-06-1994
			US	5473890 A	12-12-1995
EP 0664147	A	26-07-1995	JP	7155601 A	20-06-1995
			DE	69503527 D1	27-08-1998
			DE	69503527 T2	29-04-1999
			EP	0664147 A2	26-07-1995
			US	5849254 A	15-12-1998
			US	6217831 B1	17-04-2001
EP 0953375	A	03-11-1999	DE	19819372 A1	04-11-1999
			EP	0953375 A2	03-11-1999
			JP	11347356 A	21-12-1999
			US	6238525 B1	29-05-2001
WO 0043102	A	27-07-2000	AU	1993900 A	07-08-2000
			EP	1149231 A2	31-10-2001
			WO	0043102 A2	27-07-2000

EPO FORM P455

For more details about this annex, see Official Journal of the European Patent Office, No. 12/82




European Patent Office
10958 Berlin
GERMANY
Tel.: +49 30 259010
Fax: +49 30 25901840

Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Neath, Susannah Maini
Frank B. Dehn & Co.
St Bride's House
10 Salisbury Square
London EC4Y 8JD
GRANDE BRETAGNE



EPO Customer Services

Tel.: +31 (0)70 340 45 00

Date

18.09.07

Reference 13.91267	Application No./Patent No. 04792093.9 - 1521 PCT/JP2004014737
Applicant/Proprietor Osaka Industrial Promotion Organization	

COMMUNICATION

The European Patent Office herewith transmits as an enclosure the supplementary European search report under Article 157(2)(a) EPC for the above-mentioned European patent application.

If applicable, copies of the documents cited in the European search report are attached.

- ☒ Additional set(s) of copies of the documents cited in the European search report is (are) enclosed as well.

Refund of the search fee

If applicable under Article 10 Rules relating to fees, a separate communication from the Receiving Section on the refund of the search fee will be sent later.



EPO Form 1507.4 03.95



European Patent
Office

**SUPPLEMENTARY
EUROPEAN SEARCH REPORT**

Application Number
EP 04 79 2093

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
A	EP 1 216 746 A (DELPHI TECHNOLOGIES, INC.) 26 June 2002 (2002-06-26) * abstract; claim 14; figure 2; example 1 *	1-3,5-8	INV. B01D53/60 B01D53/44 B01D53/62 B01D53/70 B01D53/72 F01N3/08
A	US 6 374 595 B1 (B.M.PENETRANTE ET AL) 23 April 2002 (2002-04-23) * claim 14 *	1,3,5-8	
A	US 5 362 463 A (A.B.STILES ET AL) 8 November 1994 (1994-11-08) * claims *	1	
			TECHNICAL FIELDS SEARCHED (IPC)
			B01D F01N
The supplementary search report has been based on the last set of claims valid and available at the start of the search.			
Place of search Berlin		Date of completion of the search 10 September 2007	Examiner CORDERO ALVAREZ, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.92 (P04004)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 04 79 2093

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-09-2007

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
EP 1216746	A	26-06-2002	US	2002081242 A1	27-06-2002
US 6374595	B1	23-04-2002	NONE		
US 5362463	A	08-11-1994	AT	178501 T	15-04-1999
			AU	675455 B2	06-02-1997
			AU	5010093 A	15-03-1994
			CA	2140366 A1	03-03-1994
			DE	69324365 D1	12-05-1999
			DE	69324365 T2	04-11-1999
			EP	0656809 A1	14-06-1995
			JP	8503880 T	30-04-1996
			WO	9404258 A1	03-03-1994

EPO FORM P0458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82